



## XP1240 SOFT TWILL

### COMPOSITION

52% cotton / 48% polyester

### FABRIC PROPERTIES

Usable width	.	150.0 CM
Full width	Full width	155.0 CM
Weight with a deviation of 4%	EN 12127 meth 5	190 G/M <sup>2</sup>

### PROPERTIES

Tensile Strength warp	ISO13934-1 2013	1100 N
Tensile Strength weft	ISO13934-1 2013	600 N
Tear Resistance Elmendorf warp	ISO13937-1 2000	65 N
Tear Resistance Elmendorf weft	ISO13937-1 2000	19 N
Tear Strength (3 legs) warp	ISO4674 1A 2003	35 N
Tear Strength (3 legs) weft	ISO4674 1A 2003	35 N
Air Permeability 100Pa	ISO9237-2 1995	54 L/M <sup>2</sup> .S
Shrinkage oven 1min-190°C - warp	shri oven 1min	-2,00 %
Shrinkage oven 1min-190°C - weft	shri oven 1min	-0,50 %
40°C Wash		
Tumble Dry	✓	
Dry Clean	x	
Iron	✓	

### COLOURFASTS

		Light	Middle	Dark	Change
Colourfastness to light	ISO105B02 2014	4/5			

### REMARKS

Treated for transfer printing

The values on this sheet are solely indicative and are in no way binding for Xpres