



XP1241 SAGO

COMPOSITION

100% polyester

FABRIC PROPERTIES

Usable width	.	150.0 CM
Full width	Full width	150.0 CM
Weight with a deviation of 4%	EN 12127 meth 5	126 G/M ²

PROPERTIES

Tensile Strength warp	ISO13934-1 2013	750 N
Tensile Strength weft	ISO13934-1 2013	440 N
Tear Resistance Elmendorf warp	ISO13937-1 2000	12 N
Tear Resistance Elmendorf weft	ISO13937-1 2000	12 N
Tear Strength (3 legs) warp	ISO4674 1A 2003	20 N
Tear Strength (3 legs) weft	ISO4674 1A 2003	25 N
Spray Test	EN24920	100 ISO 5
Air Permeability 100Pa	ISO9237-2 1995	<30 L/M ² .S
Shrinkage oven 1min-190°C - warp	shri oven 1min	-3,50 %
Shrinkage oven 1min-190°C - weft	shri oven 1min	-3,00 %
40°C Wash		

COLOURFASTS

		Light	Middle	Dark	Change
Colourfastness to light	ISO105B02 2014	5	5	5	

REMARKS

Treated for transfer printing

The values on this sheet are solely indicative and are in no way binding for Xpres